

Please add the following claims:

-- 11. The adhesive tape of Claim 6, wherein said coating is a release coating.

12. The adhesive tape of Claim 7, wherein said application rate is 0.2 to 1.5 gm².

13. The adhesive tape of Claim 9, wherein said application rate is from 20 to 30 gm². --

REMARKS

This Preliminary Amendment is being filed to eliminate multiple dependency and to conform the claim language to proper idiomatic English.

Favorable action is respectfully solicited.

ADDITIONAL FEE

Please charge any insufficiency of fees, or credit any excess, to Deposit Account No. 14-1263.

Respectfully submitted,

NORRIS, McLAUGHLIN & MARCUS, P.A.

By 

William C. Gerstenzang

Reg. No. 27,552
220 East 42nd Street - 30th Floor
New York, New York 10017
(212) 808-0700

I hereby certify that this paper is being deposited with the United States Postal Service as Express Mail, Label No. EL767491433US to: BOX PATENT APPLICATIONS, The Hon. Commissioner of Patents, Washington, D.C. 20231 on December 28, 2000.

Norris McLaughlin & Marcus, P.A.

By 

Date: 12/28/00

MARKED-UP COPY OF AMENDED CLAIM,
SHOWING CHANGES RELATIVE TO PREVIOUS VERSION

Claim 2 (amended). The adhesive tape [as claimed in] according to claim 1, wherein the thickness[es] of the backing [are] is from 15 to 120 μm [, preferably from 20 to 50 μm].

Claim 3 (amended). The adhesive tape [as claimed in] according to claim 1, wherein the edges of the polypropylene film have a serrated cut.

Claim 4 (amended). The adhesive tape [as claimed in] according to claim 1, wherein the polypropylene film [has been] is corona treated or flame treated in order to improve the adhesion of the adhesive composition to the polypropylene film.

Claim 5 (amended). The adhesive tape [as claimed in] according to claim 1, wherein a primer layer [has been] is applied between the polypropylene film and the adhesive layer.

Claim 6 (amended). The adhesive tape [as claimed in] according to claim 1, wherein the side of the polypropylene film opposite the adhesive composition bears a coating[, especially a release coating].

Claim 7 (amended). The adhesive tape [as claimed in] according to claim 11, wherein the application rate of the release coating is from 0.1 to 3 g/m^2 [, preferably from 0.2 to 1.5 g/m^2].

Claim 8 (amended). The adhesive tape [as claimed in] according to claim 1, wherein the adhesive composition is a solventborne adhesive composition based on styrene-isoprene-styrene copolymers.

Claim 9 (amended). The adhesive tape [as claimed in] according to claim 1,
wherein the application rate of the adhesive composition is from 15 to 60 g/m²], preferably
from 20 to 30 g/m²].